



IAPMO/ANSI Z124.1.2-2005 Plastic Bathtub and Shower Units

5.2 Stain Resistance: **Pass**
Level 3 Compliance

<u>Reagent</u>	<u>Exposure Time</u>	<u>Covered Specimen Rating</u>	<u>Uncovered Specimen Rating</u>
Black Crayon	16 hrs.	2	2
Black Liquid Shoe Polish	16 hrs.	3	3
Blue Washable Ink	16 hrs.	4	3
Gentian Violet Solution	16 hrs.	4	3
Lipstick	16 hrs.	2	2
Hair Dye	16 hrs.	2	2
Iodine, 1%	16 hrs.	3	1
Total Stain Resistance Rating (50 max.):		<u>36</u>	

5.3 Cleanability & Wear: **Fail**
Level 3 Compliance

<u>Specimen</u>	<u>% Reflectance Loss (5% max.)</u>	<u>% Reflectance Loss After Additional Cleaning (2% max.)</u>	<u>Thickness, in.</u>
1	5.8%	0.7%	0.48 in.
2	4.1%	0.0%	0.48 in.
3	0.6%	0.2%	0.48 in.